

Technical Properties of: <b>ZELLAMID® 1100 MO (PA 6 C)</b>					
Edition / Date: 1 / 01-01-2016					
Characteristics		Unit	Test method	Condition of specimen	Value
<b>MECHANICAL PROPERTIES</b>					
Yield stress	23 °C	MPa	ISO 527		85
Elongation at break	23 °C	%	ISO 527		40
Tensile E-Modulus		MPa	ISO 527		3 200
Bending Modulus		MPa	ISO 178		3 500
Flexural Strength		MPa	ISO 178		140
Charpy impact strength	23 °C	kJ/m <sup>2</sup>	ISO 179/1eU		no break
Charpy Notched Impact Strength	23 °C	kJ/m <sup>2</sup>	ISO 179/1eA		≥ 5
Ball Hardness		MPa	ISO 2039-1		160
<b>THERMAL PROPERTIES</b>					
Melting Temperature		°C	ISO 3146		220
Maximum Service Temperature for Few Hours Operation		°C	-		160
Service temperature long term		°C	-		105
Minimum service temperature		°C	-		-40
Specific Heat Capacity		J/(g.K)	IEC 1006	dry	1.7
Coefficient of thermal expansion		1/K10 <sup>^-5</sup>	DIN 53752		≥ 7 ≤ 8
Thermal Conductivity	Method A	W/(K.m)	-	dry	0.23
<b>DIELECTRIC PROPERTIES</b>					
Dielectric Constant	1 MHz		IEC 60250		3.7
Dissipation Factor Tan δ	1 MHz		IEC 60250		0.03
Dielectric Strength		KV/mm	IEC 60243		50
Volume Resistivity		Ω.cm	IEC 60093		10 <sup>15</sup>
Surface Resistivity		Ω	IEC 60093		10 <sup>13</sup>
Resistance to Tracking (CTI)			IEC 60112		600
<b>PHYSICAL PROPERTIES</b>					
Density	23 °C	g/cm <sup>3</sup>	ISO 1183-1		1.15
<b>BURNING BEHAVIOUR</b>					
Flammability classification*			UL 94		HB
<b>GENERAL</b>					
Water Absorption	23 °C, saturation	%	ISO 62		6.5
	23 °C / 50% RH	%	ISO 62		2.2
Food contact			-		/
Food contact approval			FDA		/
			EU 10/2011		/
Dimensional Stability			-		-
Coefficient of Friction			-		+
Wear Resistance			-		+
<b>RESISTANCE</b>					
Chemical Resistance			-		+

Resistance to wear tested by a pin / rotating disc test according DIN ISO 7148-2 under following conditions: Ra = 0.35 - 0.45 μm (steel disc), v = 0.3 m/s, p = 3 N/mm<sup>2</sup>, time T > 16 h

Explanation Symbols: + good 0 neutral - not good / actually not available

Tests are done under dry conditions at room temperature

All statements, technical information and recommendations contained in this data sheet are presented in good faith, but all information given is without warranty and liability. Properties of the delivered products can vary because of differences to the testing samples. Non-tested values are fulfilled with raw material datas and literature information. The reader is cautioned, however that Zell-Metall cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of Zell-Metall products in any given application.